

POLYBRITE® 24 ELASTOMERIC ROOF COATING

PRODUCT DESCRIPTION

Polybrite 24 is a water-based elastomeric coating available in white or as tinted, which cures to form a seamless membrane when applied over the entire roof area. Polybrite 24 offers the unique ability to extend the life cycle of new and existing roof systems, in addition to keeping the surface cool, providing protection from ultraviolet sun and other weather exposures.

USES

- Protect and waterproof a variety of roof surfaces.
- Suitable for use on various conventional BUR and polymer modified roof membranes with smooth and mineral surfacing, sprayed polyurethane foam, most metal roof systems, Thermoplastic and Thermoset single-ply membranes, concrete, exterior-grade plywood, rigid coverboards such as Dens-Deck® and Securock®.
- Suitable for use on cementitious stucco, EIFS and other masonry surfaces.
- Application of PG 800 emulsion is a good foundation for this and other Polyglass elastomeric coatings.

FEATURES AND BENEFITS

- Polybrite 24 is compliant with the stringent standards of Cool Roof Rating Council (CRRC®) and California Title 24 (white color only).
- Extends the useful life of the roof.
- Offers excellent resistance to extended exposure to solar ultraviolet energy.
- By decreasing roof surface temperature, Polybrite 24 can reduce energy costs.
- Offers high tensile strength and elongation.
- Resistant to dirt pick up.
- Fungal and algal resistant – even in high temperatures.
- Low VOC, non-flammable and presents minimal hazard to the applicator or the environment.

TYPICAL PHYSICAL PROPERTIES

TEST PROPERTY	TEST VALUE	TEST PROCEDURE
Accelerated Weathering @ 1000 hr (pass/fail)	pass	ASTM D 4798
Permeance (perms)	13 (wet) 7 (dry)	ASTM D 1653
Fungi Resistance (pass/fail)	pass	ASTM G 21
Elongation (%)	200 +/-25	ASTM D 2370
Tensile Strength (psi)	350 +/-50	ASTM D 2370
Flexibility @ O'F mandrel (pass/fail)	pass	ASTM D 522B
Viscosity (cP)	28,000 - 58,000	Brookfield® 4d/5 RPM/77° F
Weight/gal (lb)	11 +/- .5	ASTM D 2939
Solids Weight (%)	55 +/- 2	ASTM D 1644
Solids Volume (%)	47	ASTM D 2697
VOC (gm/L)	<50	Std method
pH (rating)	>8.5	Std method
Flash Point (°F)	>212	PMCC

APPLICATION INSTRUCTIONS

Surface Preparation:

- All surfaces to receive coating must be clean, dry and free from any foreign matter such as dirt, oils, grease or other debris that could inhibit the adhesion capabilities of the newly installed products.



APPLICABLE STANDARDS

- Meets Cool Roof Rating Council standards for solar reflectance and thermal emittance (white color only)
- California Title 24 Compliant (white only)
- Energy Star® Rated (white only)



PACKAGING

- 4.75 Gallon (18.0 Liters) Pail
- 50 Gallon (189.3 Liters) Drum
- 275 Gallon (1041 Liters) Tote

POLYGLASS U.S.A., INC. MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.
1111 West Newport Center Drive
Deerfield Beach, FL 33442
www.polyglass.us
General Line: (888) 410-1375
(954) 233-1330
Customer Service: (800) 222-9782
Technical Service: (866) 802-8017

Questions? pgmarketing@polyglass.com

CRRC COOL ROOF RATING COUNCIL	Initial		Weathered	
	Solar Reflectance	*0.83	Pending	
Thermal Emittance	*0.88	Pending		
Solar Reflectance Index (SRI)	*104	Pending		
Rated Product ID Number	0616-0012			
Licensed Seller ID Number	0616			
Classification	Field Applied Coating			

Cool Roof Rating Council ratings are determined for a fixed set of conditions, and may not be appropriate for determining seasonal energy performance. The actual effect of solar reflectance and thermal emittance on building performance may vary.
Manufacturer of product stipulates that these ratings were determined in accordance with the applicable Cool Roof Council procedures.
* Reported values are applicable to White color only.



1-800-222-9782
www.polyglass.us

POLYBRITE® 24

ELASTOMERIC ROOF COATING

- Metal surfaces that display rusting or other oxidation, to be prepared with a grinder or wire brush as needed to remove surface contaminants.
- Existing roof systems to be visually inspected for conditions that may adversely affect adhesion or performance of newly installed products. Repair any visible deficiencies such as splitting, blistering, and buckling.
- Visually inspect all metal and non-metal flashings, edges, drains, valleys and through-roof penetrations and repair as needed by project conditions.
- Do not apply to wet or visibly damp surfaces, or surfaces previously covered with coal tar based products or Kynar® finishes.
- Concrete surfaces cured with wax/resin based compounds can inhibit adhesion.

Application:

- Stir well prior to application. To field tint this product, please use a water-based, exterior-grade pigment.
- Polybrite 24 may be applied by high pressure spray, roller or brush application methods.
- Apply Polybrite 24 at 24 wet mils (1.5 gallon per 100 square feet) per coat. Typical application conditions require Polybrite 24 be applied in two coats at 24 wet mils per coat.
- Allow coating to dry overnight prior to applying second coat.
- To minimize potential voids or pinholes in coating application, apply second coat perpendicular to the first.
- Apply only when ambient temperatures are 50°F and rising. Cold weather could result in uneven application and improper curing of product. Do not apply if there is a threat of inclement weather within 24 hours of application.
- Do not thin product. Do not heat outside of container. Do not apply at temperatures greater than 120°F.
- When coating over newly-applied asphalt emulsion, proceed as soon as the emulsion has cured, normally 1 to 5 days (follow instructions for PG 800 Asphalt Emulsion).
- Prior to using this product on new cap sheets (smooth or granulated), it is recommended to wait 30 days for weathering. Newly applied PG 800 Asphalt Emulsion can typically be coated once emulsion has cured, usually 1 to 5 days depending on weather and rate of emulsion application.

Storage and Cleaning:

- Product shelf life: 18 months from date of manufacture when properly stored.
- Do not store at temperatures greater than 120°F.
- Store 24 hours at room temperature prior to application.
- Observe normal safeguards for storing and handling of this product prior to and during application.
- Do not allow product to freeze. Discard if any degree of freezing would occur.
- Keep containers covered when not in use.
- Clean equipment and overspray with water.
- Clean hands with waterless hand cleaner.

WARNING

Personal Protection - Irritation may result from prolonged or repeated contact with skin. Wear chemical resistant gloves, protective goggles and protective clothing, if needed.

Eye Contact - Rinse immediately with clean water for 15 minutes and seek medical advice.

Waste Disposal - Empty containers must be disposed of in accordance with local, state and federal regulations.

For Professional Use Only - Keep out of the reach of children.

Refer to material safety data sheet (MSDS) for specific data and handling of our products.

All data furnished refers to standard production using manufacturing testing tolerances. The product user, and not Polyglass, is responsible for determining the suitability and compatibility of our products for the user's intended use.



1-800-222-9782
www.polyglass.us

For the most current product data and warranty information, visit www.polyglass.us