



- SURFACE COAT                      POLYBRITE 70 OR PG 700 ELASTOMERIC ROOF COATINGS. APPLY A MINIMUM OF 2 COATS.
- BASE COAT                            POLYBRITE 70, POLYBRITE 76, OR PG 700 ELASTOMERIC ROOF COATINGS. APPLY A MINIMUM OF 2 COATS.
- FLASHING COMPOUND              POLYBRITE 72 FLASHING COMPOUND. APPLY AT 1/8" THICK AND USE WITH POLYESTER REINFORCEMENT.
- POLYESTER                            POLYBRITE REINFORCING POLYESTER.
- SURFACE PREPARATION            IF OXIDATION IS PRESENT, GRINDING AFFECTED AREAS WITH WIRE BRUSH IS NECESSARY. THEN PRIME ENTIRE ROOF WITH POLYBRITE 74 RUST INHIBITOR PRIMER APPLIED AT THE RATE OF 18-24 WET MILS (150-180 SQUARE FEET PER GALLON).

TYP. CURB  
FLASHING DETAIL

NUMBER:

PG-CFD-012

DATE:

MARCH 2014



www.polyglass.com