



- SURFACE COAT

POLYBRITE 70 OR PG 700 ELASTOMERIC ROOF COATINGS. APPLY A MINIMUM OF 2 COATS.

- BASE COAT

POLYBRITE 70, POLYBRITE 76, OR PG 700 ELASTOMERIC ROOF COATINGS. APPLY A MINIMUM OF 2 COATS.

- FLASHING COMPOUND

POLYBRITE 72 FLASHING COMPOUND WHERE REQUIRED. APPLY AT 1/8" THICK AND USE WITH POLYESTER REINFORCEMENT.

- POLYESTER

POLYBRITE REINFORCING POLYESTER.

- SURFACE PREPARATION

ENSURE SURFACES ARE FREE OF ANY SURFACE CONTAMINATES. IF OXIDATION IS PRESENT, GRINDING AFFECTED AREAS WITH WIRE BRUSH IS NECESSARY. THEN PRIME ENTIRE ROOF WITH POLYBRITE 74 RUST INHIBITOR PRIMER APPLIED AT THE RATE OF 18-24 WET MILS (150-180 SQUARE FEET PER GALLON).

## STANDARD PARAPET AND ROOF DRAIN DETAIL

NUMBER:

PG-PRD-002

DATE:

MARCH 2014



www.polyglass.com